

MDPE Temperature Derate Pressure Chart

MDPE PE 2708 Design Pressure (psi)					
Operating Temperature					
Application	DR	73°F	100°F	120°F	140°F
Regulated Natural Gas 49 CFR 192 Applications	DR 7	125	125	125	107
	DR 9	125	100	100	80
	DR 9.33	120	96	96	77
	DR 10	111	89	89	71
	DR 11	100	80	80	64
	DR 11.5	95	76	76	61
	DR 13.5	80	64	64	51
	DR 15.5	69	55	55	44
<small>Gas distribution and transmission pressure ratings per 49 CFR Part 192, s12" PE pipe meeting minimum wall thickness requirements per §192.121 and produced after January 22, 2019</small>					

P & F

DISTRIBUTORS

**"HDPE PIPE
IS OUR BUSINESS"**